

Roadlab Laboratories (Pty) Ltd

Civil Materials Testing **BBBEE Level 1** Contributor

Registration No: 2011/005423/07

VAT No: 4670261090

Cape Town ,7530

> material Passion.> trusted Accuracy.> timeous Excellence.

CLIENT: WORLD OF DECORATIVE CONCRETE

ATTENTION: JOHAN COETZEE

TEST REPORT

 Job No
 CTC05246

 Ref. No

Date 05-09-2023

 Tested/Sampled By:
 ROADLAB

 Date Sampled / Received
 04-09-2023

 Date Tested
 05-09-2023

 Sampling Method *
 SABS 1215:2008

 Test Method
 SABS 1215:2008

Project

Test Type COMPRESSIVE STRENGTH TEST REPORT

Sampled By ROADLAB
Delivered By ROADLAB

Temp. °C

Laboratory Tester JOSHUA EVERTS
Environmental Conditions COLD & WINDY
Remarks / notes NONE
Number of pages 2

Special instructions

NONE

Remarks:

- 1. Opinions & Interpretations are not included in our scope of works.
- 2. The samples were subjected to analysis according to test method (SANS).
- 3. The test results reported relate to the samples tested.
- 4. Further use of the above information is not the responsibility or liability of Roadlab.
- 5. Documents may only be reproduced or published in their full context.
- 6. Samples brought in by clients may have an effect on the validity of the test results.

Mr. W Mathobela Technical Signatory



Roadlab Laboratories (Pty) Ltd

Civil Materials Testing **BBBEE Level 1** Contributor

Registration No: 2011/005423/07

VAT No: 4670261090

→ +27 21 949 0701
 □ info@roadlab.co.za
 ♠ 1 Palmiet Road,
 Stikland Industrial,

Cape Town ,7530

TEMP.'C. INSIDE LABORATORY

material Passion.trusted Accuracy.timeous Excellence.

JOB NO CTC05246 Your Ref: - Date: 05-09-2023

CLIENT: WORLD OF DECORATIVE CONCRETE

ATTENTION: JOHAN COETZEE

SAMPLES COLLECTED BY:

COMPRESSIVE STRENGTH TEST REPORT SANS 1058:1985

CONTRACT: PRESS SERIAL NUMBER: 213/65

216x112mm SOLID MAXI BRICKS

LOCATION: WHITE CEM SCALE SERIAL NUMBER:

SPECIFIED STRENGTH: NOT SPECIFIED DATE RECEIVED: 04-09-2023

MASONRY SUPPLIER: NOT SPECIFIED DATE IMMERSED IN WATER: SAMPLES WHERE MADE BY: ROADLAB TIME IMMERSED IN WATER: -

LABORATORY TESTER: JOSHUA EVERTS ENVIRONMENTAL CONDITIONS COLD & WINDY

ENGINEER'S SPECIFICATIONS: NOT SPECIFIED CURING TANK TEMP.

ROADLAB

Water Size (mm) Compressive Strength Laboratory Age Mass (g) Mass (g) After Your Reference Date Cast Date Tested Faktor Absorption Load (kN) Days Before soaking (MPa) Number soaking (%) w 23/B/2029 05-Sep-23 216 112 24,19 486 20,1 89

Average
Standard Deviation

Remarks:

- 1. Opinions & Interpretations are not included in our scope of works.
- 2. The samples were subjected to analysis according to test method (SANS).
- 3. The test results reported relate to the samples tested.
- 4. Further use of the above information is not the responsibility or liability of Roadlab.
- 5. Documents may only be reproduced or published in their full context.
- 6. Samples brought in by clients may have an effect on the validity of the test results.

Mr. W Mathobela Technical Signatory

20,1

486